

Ultrex CW

An immersion oxidizing material for copper-based alloys, white metal, tin-lead alloys and silver.

Ultrex CW is a concentrated, mildly acidic, non-sulfide containing liquid material formulated to produce an oxidized finish on a variety of base metals by simple immersion at room temperature. By varying the operating concentration of the Ultrex CW, a range of color tones, from brown to purple, to gray black, can be obtained. These colors may be obtained by immersion of the parts or by wiping the Ultrex CW onto the parts to be oxidized. The tone and adhesion of the Ultrex CW immersion deposit will also be influenced by the base metal being treated. The most uniform and adherent finishes will be produced on thoroughly clean solid brass, copper, or silver. Plated parts can also be treated in the Ultrex CW solution provided the plated coating is of enough thickness. To obtain uniform finishes on plated parts, the plated deposit should be relatively uniform.

The surface finish produced by the Ultrex CW solution is extremely thin and can readily be obtained by tumbling, steel wool wiping, scratch brushing or mechanical polishing. Unique and interesting "antiqued" and "highlighted" finishes are produced in this matter.

Applications for the Ultrex CW solution include antiquing for Tiffany lamps, buttons, ornaments, hardware components, etc. Ultrex CW can also be used to produce antique pewter effects, for color coding of parts and as a final uniform finish. Since the Ultrex CW deposit is quite thin and has little corrosion resistance, parts treated with Ultrex CW should be lacquered for maximum service.

Operating Conditions

Concentration	1-part Ultrex CW:4 – 8 parts water
Temperature	75°F – 90°F
Immersion Time	30 seconds - 3 minutes depending on concentration and tone desired
Equipment	Plastic, fiberglass, or rubber-lined tanks
Control	Dip may be controlled by small additions (1 to 2 fl oz/Gal) of



Cleaning
the Hard to Clean



Finishing
the Hard to Finish



Treating
the Hard to Treat

	concentrated Ultrex CW. When the time interval to produce the desired tone becomes inordinately long and further additions of Ultrex CW do not increase rate of color production, the bath is spent and should be replaced.
--	---

Caution

If taken internally, Ultrex CW is poisonous. Antidote: induce vomiting; when vomit fluid is clear, give 2 tablespoons of Epsom salt or milk of magnesia in water. Get medical attention. Avoid contact with skin and eyes. Use protective clothing (rubber gloves) when handling this material. In case of contact with skin, affected area should be thoroughly flushed with water for at least 15 minutes and obtain medical attention. Avoid contact of Ultrex CW with concentrated acids or oxidizing materials.

WARRANTY: THE QUALITY OF THIS PRODUCT IS GUARANTEED ON SHIPMENT FROM OUR PLANT. IF THE USE RECOMMENDATIONS ARE FOLLOWED, DESIRED RESULTS WILL BE OBTAINED. SINCE THE USE OF OUR PRODUCTS IS BEYOND OUR CONTROL, NO GUARANTEE EXPRESSED OR IMPLIED IS MADE AS TO THE EFFECTS OF SUCH USE, OR THE RESULTS TO BE OBTAINED.

Our people. Your problem solvers.

For more information on this process please call us at

1-800-648-3412

or techservice@hubbardhall.com

